

GEARTRON

GEAR OILS

FLEXOR 75W-80 MTF



GEARTRON RANGE

9 products · 6 grades

SAE 75W	1	SAE 75W-80	2
SAE 75W-90	2	SAE 75W-140	1
SAE 80W-90	2	SAE 85W-90	1

SPECIFICATIONS · SAE 75W-80

- API GL-4
- ZF TE ML 01L 02L 08 13 24A 16K
- MB 235,10
- BMW MTF LT2/LT3/LT4
- GM 1940182
- GM 1940768
- MAN 341 E3
- MAN 341 Type Z4
- FIAT 9.55550-MZ12
- RENAULT B0032/2 Annex3 DC4/DW5
- DAF EATON PS-321
- FORD WSD M2C200-D /WSS-M2C200-D2/WSS-M2C186-A
- PSA B712330/9730AB / B712316/B712315
- RENAULT NISSAN MITSUBISHI MTF-DW5
- RENAULT NISSAN MITSUBISHI TRZ/TRJ/TRT/TRP/NFP/TRX
- RENAULT NISSAN MITSUBISHI MT-XZ / MTXZ TL
- VW G052527 / G052726 / G052512 / 5052171 / G052317 / G060726 / G055512
- VW 5052178 / G052171 / G052178 / G052549
- VOLVO 97305/ 97307/97308/ 97309/97310

SAE 75W-80 Gear Lubricant for Mechanical Transmissions

SAE 75W-80 lubricant for mechanical transmission systems that require this specific viscosity grade. Selected according to the specifications of the gearbox manufacturer.

KEY ADVANTAGES

- Optimised synchroniser performance
- Very high thermal and oxidative stability
- Maximum resistance to wear
- Maximum compatibility with materials used in these systems
- Low pour point

PACK	CODE	UNITS / BOX	PER PALLET
1 L	GDEK50801	18	54 boxes
4 L	GDEK50844	4	60 boxes
20 L	GDEK50820	—	48 units
60 L	GDEK50860	—	18 units
208 L	GDEK508208	—	4 units

GEARTRON

GEAR OILS

FLEXOR 75W-80 MTF

TYPICAL CHARACTERISTICS

Property	Unit	Method	Typical value
Colour	-	Visual	Amber
Appearance	-	Visual	Limpid
Density	kg/dm ³	ASTM D7042	0,855
Kinematic viscosity at 40°C	cSt	ASTM D445	59,5
Kinematic viscosity at 100°C	cSt	ASTM D445	10,5
Brookfield viscosity at -40°C	mPa·s	ASTM D2983	80000
Viscosity Index	-	ASTM D2270	168
Flash Point	°C	ASTM D92	222
Pour Point	°C	ASTM D97	-46

MODE OF USE

Use in accordance with the recommendations in the user and maintenance manual supplied by the manufacturer. Store in a cool, dry place, protected from direct sunlight and at temperatures not exceeding 60°C (140°F).

SAFETY AND ENVIRONMENT

Use in accordance with the recommendations provided in the Safety Data Sheet. Additional information on MSDS.