

GEARTRON

GEAR OILS

ZENTORA 75W-90 LS



GEARTRON RANGE

9 products · 6 grades

SAE 75W	1	SAE 75W-80	2
SAE 75W-90	2	SAE 75W-140	1
SAE 80W-90	2	SAE 85W-90	1

SPECIFICATIONS · SAE 75W-90

- API GL-5 LS
- API GL-4
- API MT-1
- SAE J2360
- MB 235.11
- MB 235.8
- DTFR 12B140
- MAN 341 Z2 TYPE E2/E3
- MAN 342 TYPE M1/M2/M3
- MAN M 343 TYPE S1
- FORD M2C200C
- FORD ESD-M2C175A
- ARVIN MERITOR 076-A
- MACK GO-J
- MACK GO-J PLUS
- SCANIA STO 1:0
- SCANIA 2:0G
- SCANIA STO 2:0AFS
- MIL L-2105 C/D
- MIL PR-2105E
- VOLVO 97312
- ZF TE-ML
- 02B/05B/08/12B/17B/17C/21A/21B
- SFU IVECO 18-1805 CLASSE RAS1

Ester-Based Synthetic Lubricant for Limited-Slip Differentials

Ester-based synthetic SAE 75W-90 for limited-slip differentials (LS/LSD) of passenger cars, SUVs and commercial vehicles. The friction-control and wear-protection formulation is aimed at API GL-5 LS applications. Use in a manual gearbox only if specified by the manufacturer.

KEY ADVANTAGES

- Outstanding friction control
- Very high thermal and oxidative stability
- Maximum resistance to wear
- Maximum compatibility with materials used in these systems
- Low pour point

PACK	CODE	UNITS / BOX	PER PALLET
1 L	GDEK51001	18	54 boxes
4 L	GDEK51044	4	60 boxes
20 L	GDEK51020	—	48 units
60 L	GDEK51060	—	18 units
208 L	GDEK510208	—	4 units

GEARTRON

GEAR OILS

ZENTORA 75W-90 LS

TYPICAL CHARACTERISTICS

Property	Unit	Method	Typical value
Colour	-	Visual	Amber
Appearance	-	Visual	Limpid
Density	kg/dm ³	ASTM D7042	0,862
Kinematic viscosity at 40°C	cSt	ASTM D445	92
Kinematic viscosity at 100°C	cSt	ASTM D445	16,2
Viscosity Index	-	ASTM D2270	190
Flash Point	°C	ASTM D92	22
Pour Point	°C	ASTM D97	-48

MODE OF USE

Use in accordance with the recommendations in the user and maintenance manual supplied by the manufacturer. Store in a cool, dry place, protected from direct sunlight and at temperatures not exceeding 60°C (140°F).

SAFETY AND ENVIRONMENT

Use in accordance with the recommendations provided in the Safety Data Sheet. Additional information on MSDS.